

# UDC-2

Photopolymer dual cure direct emulsion for the broadest range of applications.

## MATERIALS

Required	Recommended
Exposure unit	Drying cabinet
Washout sink	Pressure washer
Clean work area	Chromaline Exposure
Scoop coater	Calculator

## CHEMICALS

Required	Recommended
Chroma/Clean™ mesh degreaser	Chroma/Haze™ haze remover
Chroma/Strip™ screen reclaimer	

## SAFETY AND HANDLING

Avoid contact with skin and eyes. Refer to MSDS for further information.

## SPECIFICATIONS

<b>Appearance:</b>	Blue
<b>Exposure:</b>	fast (see reverse)
<b>Solids:</b>	38% (after sensitized)
<b>Other:</b>	available upon request

### **Standard Sizes**

Quart, gallon, 3.5 gal., 50 gal. drum

## STORAGE

**Sensitized UDC-2 emulsion** has a shelf life of 3 to 4 weeks at room temperature (60 to 80°F). To maximize sensitized shelf life use only distilled water to dissolve diazo sensitizer.

**Protect from freezing.** UDC-2 is not freeze/thaw stable. Freezing during shipping may result in clear gel spots which may resemble pinholes.

**Coated, unexposed screens** can be stored as long as one month in a clean, cool, dry and completely dark area.

**Expiration date.** Always check the expiration date on sensitizer bottle and emulsion bucket to assure freshness.

## ▼ **Magna/Cure UDC-2**

UDC-2 dual cure emulsion is designed for the widest range of imaging applications. UDC-2 provides these additional benefits:

- Excellent definition and line edge
- Blue color offers excellent contrast yet easy registration
- Highest buildup proud of mesh with low Rz values



▼  
**Magna/Cure UDC-2** direct emulsion allows screen makers to obtain remarkable image quality and exceptionally durable stencils.

*For use with water, solvent, co-solvent, UV and plastisol based inks. Available in both clear and dyed formulations.*



### **Chromaline Screen Print Products**

4832 Grand Ave. • Duluth, Minnesota 55807 • Tel: 218-628-2217 • FAX: 218.628.3245  
Web Site: [www.chromaline.com](http://www.chromaline.com) • E-mail: [sales@chromaline.com](mailto:sales@chromaline.com)

# UDC-2

## Instructions

Work under yellow lights



### DEGREASE

Using Chroma/Clean™ mesh degreaser, work up a lather on both sides of mesh. Flood screen and frame thoroughly with garden type hose, then dry.



### MIX

Mix emulsion and sensitizer according to instructions on bottle. Let emulsion stand at least two hours before using.


### COAT

Fill scoop coater with room temperature emulsion. Slowly apply first coat to print side. Then coat squeegee side with one to three coats depending upon thickness required. If thicker stencil is required, additional coats may be applied to print side after initial drying of stencil. Be sure to dry thoroughly between coats.




### DRY

Thoroughly dry screen in horizontal position, print side down, using a dark, clean drying cabinet. Temperature should not exceed 104°F (40°C).



### EXPOSE

Place emulsion side of photopositive in contact with print side of screen.



### DEVELOP

Gently spray both sides of screen with tepid water, wait 30 seconds then gently wash print side of the screen until image is fully open. Rinse both sides thoroughly. Dry screen completely and you are ready to print.



### RECLAIM

Apply Chroma/Strip™ screen reclaimer to both sides of screen. Scrub area to be reclaimed with a stiff nylon brush to ensure entire surface is wet and let it work a few moments until stencil begins to dissolve. Remove stencil residue with pressure washer, then rinse with garden type hose, thoroughly flooding screen and frame.



## EXPOSURE GUIDELINES

**Note: Exposure times are suggested only as a guide. Use the Chromaline Exposure Calculator to determine optimal exposure times.** Individual exposure times may vary depending upon equipment used, bulb age, and other shop conditions.

### SUGGESTED MINIMUM EXPOSURE GUIDELINES

Mesh	Time
158 mesh	60 - 90 sec. 379 - 556 mj/cm <sup>2</sup>
230 mesh	45 - 60 sec. 253 - 379 mj/cm <sup>2</sup>
305 mesh	30 - 45 sec. 165 - 253 mj/cm <sup>2</sup>

Exposure times were set for a 5KW unit at 42" from the frame. All screen mesh was orange in color. Screens were coated wet on wet once on print side and twice on squeegee side.

**AVOID FAILURE:** Dual cure emulsions have a very wide exposure latitude. Underexposed stencils often appear acceptable, but premature breakdown can occur on the press. When determining exposure speed, always overexpose your test stencil, then reduce exposure time until acceptable image quality is achieved. This will help assure good durability.

FOR TECHNICAL SERVICE  
Call Toll Free 1-800-328-4261